

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	CLASS	LIGHT ISO 105-B02	WASHING 40°C ISO 105-C01			WATER ISO 105-E01			SEA WATER ISO 105-E02			ACID PERSPIRATION pH 5.5 ISO 105-E04			ALKALINE PERSPIRATION pH8.0 ISO 105-E04			CHLORINATED WATER ISO 105-E03			
			C.C	S.Co	S.Pa	S.PI	S.Co	S.Pa	S.PI	S.Co	S.Pa	S.PI	S.Co	S.Pa	S.PI	S.Co	S.Pa	S.PI	50mg/l C.C	100mg/l C.C	
0028 BIANCO	class 1	3-4	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	3-4	3
0086 AVORIO	class 1	>5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	4	3-4
0165 BRULE	class 1	>5	5	4-5	5	5	4-5	5	5	4-5	5	5	4-5	5	5	4-5	5	4	2-3		
0191 PLANET	class 1	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	1-2	
0215 TOFFEE	class 1	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	1	
0240 MAKE-UP	class 1	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	3-4	
1228 LUSO	class 1	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	2-3	
2160 INCAS	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	3	
2210 DAIQUIRI	class 1	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	2	
2212 CHARLESTON	class 1	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	3-4	1	
3149 CLEMATIS	class 1	3-4	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
3250 FIABA	class 1	3	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	2	
3280 FLIRT	class 1	2-3	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	2-3	
30010 VALZER	class 1	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	1	
30012 ALCHIMIA	class 1	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	1	
30015 COFFEE CREAM	class 1	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	1	
30032 IBRIDO	class 1	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	1	
4073 VENERE	class 2	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5
4209 COSMOPOLITAN	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	2	
4223 BOLERO	class 2	>5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	2-3
4243 SHANGHAI	class 1	5	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	2-3	1	
4260 KENYA	class 1	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	1	
5230 TURNADOT	class 2	>5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	3	1-2	
5269 ALIEN	class 2	3	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	1-2	
5716 PURPLE	class 2	>5	4-5	4	4-5	3-4	2-3	3-4	3	2-3	2-3	3-4	2-3	3-4	3	2-3	3	3	3	1-2	
50019 UPERNATURAL	class 1	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	1-2	
6005 TURCHESE	class 2	3	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	2	
6007 BLU SCURO	class 1	>5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	
6205 OLTREMARE	class 1	4-5	5	5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	3-4	1-2	
6266 BAIA	class 2	3	4-5	5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	3	2	
60081 TENERIFE	class 2	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	1-2	
60108 BLUE REBEL	class 2	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	2	
60201 ARIA	class 1	2	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	1	
60203 RIVA	class 1	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	1	
60264 ISOLA	class 2	>5	4-5	4	4-5	4	3	4	4	3	4	4	3	4	4	3	4	3	4	2-3	1-2
60266 SAMANA	class 2	5	4-5	4-5	4-5	4	3	4	4	3	4	4	3	4	4	3	4	3-4	4	2-3	1-2
60268 RELAX	class 2	2	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	2	
7110 IRELAND	class 2	4	4	4-5	4-5	3-4	3-4	4-5	3	3-4	4	3-4	3-4	4-5	3	3-4	4-5	4	3-4	3	
7863 JADE	class 2	3-4	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	3-4	3	
70015 BLU FONDALE	class 1	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	1-2	
70060 ARMY	class 1	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	1-2	
70146 PURO	class 1	2	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	2	
70143 MEDITATION	class 2	3-4	4	4	4-5	4	3	4	4	3-4	4	4	3	4	4	3-4	4	3-4	4	3	1-2
70180 PASCOLO	class 1	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	1-2	
8101 SEPIA	class 2	>5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	2-3	
8165 DATTERO	class 2	>5	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	2-3	
9040 NERO	class 2	>5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	3-4	3	
9154 TITANIUM	class 2	>5	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3	
9210 FILIGRANA	class 1	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	1-2	
90046 STREET	class 1	>5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3	1-2	
NEONS																					
1094 SIRIO	class 2	1-2	4	4	4	3	3	4	3	3	3-4	3	3	3-4	3	3	3-4	3	3	1	1
3015 ROSA SHOCKING	class 2	1-2	4	4	4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	1	1
3099 DAFNE	class 2	1	5	5	5	3-4	3-4	4	3-4	3-4	4	3-4	3-4	4	3-4	3-4	4	3-4	2	1	
3279 APRIL PINK	class 2	1-2	4-5	4-5	4-5	4	4	4	4	4	4	4	4	4	4	4	4	4	1	1	
30009 INFLUENCER	class 2	1-2	4-5	4-5	4-5	4	4	4	3-4	3-4	3-4	4	4	4	4	4	4	4	1-2	1	
30013 DESTINY	class 2	1-2	4-5	4-5	4-5	4	4	4	4	4	4	4	4	4	4	4	4	4	1	1	
50007 JEWEL	class 1	1-2	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	1-2	
70136 PAPPAGALLO	class 2	1	4-5	4-5	4-5	4	4	4	3	3	4	3-4	3-4	4	3	3	4	2	1		

C.C: Colour Change.
 S.Co: Staining on Cotton.
 S.Pa: Staining on Nylon.
 S.PI: Staining on Polyester.

Testing procedure OEKO-TEX® STANDARD 100 Class 1 and Class 2, please refer to www.oeko-tex.com for more information.

● Colour dyed with a particular fluoro dyestuff that might create a 'blue stains' effect in conditions of high humidity and temperature. This effect can be eliminated: machine wash the garment with soap at 30°C, delicate tumble dry or hang dry.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		

