

PURA BIOPOLISHED COTTON

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT AS2001.4.21		RUBBING AS2001.4.3		WASHING AS2001.4.15				WATER AS2001.4-E01				PERSPIRATION AS2001.4-E04			
	C.C	Dry	Wet	C.C	S.Pa	S.Co	S.PI	C.C	S.Pa	S.Co	S.PI	C.C	S.Pa	S.Co	S.PI	
PURA - COTTON 210GSM	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	
WHITE	4	3-4	2-3	4-5	4	3-4	4	4-5	4	3-4	4	4-5	4	3-4	4	
CRIMSON	3	4-5	4	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	
PIROUETTE PINK	3-4	4-5	3-4	4-5	4	4-5	4-5	4-5	2-3	4	4	4-5	3	4	4	
MAUVE	3-4	3-4	2-3	4	4	4		4	4	4		4	4	4		
FUCHSIA	3	4	3	4	4	4-5		4	4	4-5		4	4	4-5		
COBALT	5	3-4	2-3	4-5	4	4	4	4-5	3	3	3-4	4-5	3-4	2-3	4	
MARINE	4-5	4	2-3	4-5	4	4	4	4-5	4	4	4	4-5	4	4	4	
NAVY	4	3-4	2	4-5	4	4	4-5	4-5	3	3-4	4	4-5	3-4	3	4	
JET BLACK	3-4	4-5	4	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	
NUDE	2-3	3	2	4	4	3-4		4	4	4		4	4	4-5		
BOTTLE	4	3-4	2-3	4-5	4	3-4	4	4-5	3	3-4	4	4-5	4	3-4	4	
DEEP BROWN																

PURA BIOPOLISHED COTTON HEAVY

COLOUR	LIGHT AS2001.4.21		RUBBING AS2001.4.3		WASHING AS2001.4.15				WATER AS2001.4-E01				PERSPIRATION AS2001.4-E04			
	C.C	Dry	Wet	C.C	S.Pa	S.Co	S.Pe	C.C	S.Pa	S.Co	S.Pe	C.C	S.Pa	S.Co	S.Pe	
PURA - COTTON 210GSM	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	
WHITE	5	3	2	4-5	4	4	4-5	4-5	3	3	4	4-5	3	2-3	4	
JET BLACK																

- C.C: Colour Change.
- S.Co: Staining on Cotton.
- S.Pa: Staining on Nylon.
- S.PI: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		