

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT ISO 105-B02	WASHING	WATER ISO 105-E01			PERSPIRATION ISO 105-E04				RUBBING ISO 105-X12		
	C.C	C.C	C.C	S.Pa	S.Co	S.Pe	C.C	S.Pa	S.Co	S.Pe	Dry	Wet
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
PIROUETTE PINK	3-4	5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5
CHALK	3-4	4.5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
HEAVENLY	4	4.5	4-5	4	4-5	4	4-5	4	4-5	4	4-5	4
PIGEON	4	4.5	4-5	4	4-5	4	4-5	4	4-5	4	4-5	4
SPA	3-4	4	4-5	4	4	4	4-5	4	4	4	4-5	4
SAGE	4-5	5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4
EGGSHELL	4	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
TAUPE	4	4	4-5	4	4-5	4	4-5	4	4-5	4	4-5	4
GRAPHITE	4	4	4-5	3-4	4-5	4-5	4-5	4	4-5	4-5	4-5	3-4
MARINE	4-5	4	4-5	4	4-5	4-5	4-5	4	3-4	4-5	4	2-3
JET BLACK	4-5	4	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4	3

C.C: Colour Change.
S.Co: Staining on Cotton.
S.Pa: Staining on Nylon.
S.Pl: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		