

**COLOUR FASTNESS**

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT ISO 105 B02	RUBBING ISO x10		WASHING 50oc ISO			WATER ISO 105 E01			PERSPIRATION ISO 105 E04			
		C.C	Dry	Wet	S.Co	S.Pa	S.Pl	C.C	S.Co	S.Pa	S.Pl	Acid	Alkaline
<b>210GSM</b>													
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
NAVY	5-6	3	2	3	2-3	2-3	4-5	3	3-4	4	4-5	3	
FILM	4-5	4	3	3	3	3	4-5	4-5	3-4	4-5	4-5	4-5	
KENYA	5	4	3	3	3	3	4-5	3	3-4	4-5	4-5	3	
CORNFLOWER	5	4	3	3	3	3	4-5	4	3	4	4-5	4	
VALZER	5	4	3	3	3	3	4-5	4-5	4	4-5	4-5	4-5	
COBALT	5	4	3	3	3	3	4-5	4-5	3-4	4	4-5	4-5	
AMPOLLA	4-5	4	3	3	3	3	4-5	4-5	4	4-5	4-5	4-5	
NUDE	4-5	4	4	4	4	4	4-5	4-5	4-5	4-5	4-5	4-5	
VINTAGE	4-5	4	3	3	3	3	4-5	4	4	4-5	4-5	4	
BLACK	5	3	2	3	2-3	2-3	4-5	4	4	4-5	4-5	4-5	
ARMY	5	4	3	3	3	3	4-5	4-5	4	4-5	4-5	4-5	
PIROUETTE PINK	4-5	4	3	3	3	3	4-5	4-5	4-5	4-5	4-5	4-5	
SEPPIA	4	3	2	3	2-3	2-3	4-5	3	4	4-5	4-5	4-5	
MARINE	4-5	3	2	3	2-3	2-3	4-5	4-5	3-4	4-5	4-5	4-5	
<b>280GSM</b>													
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
BLACK	5	3	2	3	2-3	2-3	4-5	4	4	4-5	4-5	4-5	

- C.C: Colour Change.
- S.Co: Staining on Cotton.
- S.Pa: Staining on Nylon.
- S.Pl: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		