

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT 20H	RUBBING ISO 105 S12		WASHING		WATER ISO 105 E01			PERSPIRATION	
	C.C	Dry	Wet	C.C	C.C	S.Co	S.Pa	S.PI	Acid	Alkaline
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
PEWTER	4	4-5	4-5	4	4-5	4-5	4	4-5	4	4
HUNTER	4	4	4	3	4-5	4-5	3-4	4-5	4	4
BLACK	4	4-5	4	3	4-5	4	3-4	4-5	4	4
ESPRESSO	4	4-5	4	4	4-5	4-5	4	4-5	4	4
NAVY	4	4	4	4	4-5	4	3-4	4	3-4	3-4
IVORY	4	4-5	4-5	4	4-5	4-5	4-5	4-5	4	4
OXFORD	4	4-5	4	4	4-5	4	3-4	4	4	4
ALMOND	4	4-5	4-5	4	4-5	4-5	4-5	4-5	4	4
ELM	4	4-5	4-5	4	4-5	4-5	4	4-5	4	4

C.C: Colour Change.
S.Co: Staining on Cotton.
S.Pa: Staining on Nylon.
S.PI: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		