

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT ISO 105 B02	RUBBING ISO 105 X12		WASHING ISO 105 C06	WATER ISO 105 E01	PERSPIRATION ISO 105 C04		SALT WATER ISO 105 E03	CHLORINE SENSITIVITY ISO 105 E03
		Dry	Wet			Acid	Alkaline		
	C.C			C.C	C.C			C.C	C.C
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
SKINTONE	3-4	4	3-4	4	4	4	4	3-4	3-4
BLACK	3-4	3-4	3-4	4	4	4	4	3-4	3-4

- C.C: Colour Change.
S.Co: Staining on Cotton.
S.Pa: Staining on Nylon.
S.Pl: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		