

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT ISO 105-B02	CROCKING ISO 105-X12		WASHING 40 °C ISO 105-C01		WATER ISO 105-E01		SEA WATER ISO 105-E02		ACID PERSPIRATION PH 5.5 ISO 105-E04		ALKALINE PERSPIRATION PH 8 ISO 105-E04		CHLORINE SENSITIVITY ISO 105-E03	
		Dry	Wet	S.Co	S.Pa	S.Co	S.Pa	S.Co	S.Pa	S.Co	S.Pa	S.Co	S.Pa	50mg/l	100mg/l
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
NUDE	4	4-5	4-5	5	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	1-2	1
BLACK	>5	4-5	3-4	4-5	4-5	4-5	4	4-5	4	4-5	4	4-5	4	4-5	4

- C.C: Colour Change.
- S.Co: Staining on Cotton.
- S.Pa: Staining on Nylon.
- S.Pl: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		