

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	OEKO-TEX® STANDARD 100	LIGHT ISO 105-B02	CROCKING ISO 105-X12		WASHING 40°C ISO 105-C01			WATER ISO 105-E01			SEA WATER ISO 105-E02			ACID PERSPIRATION pH 5.5 ISO 105-E04			ALKALINE PERSPIRATION pH8.0 ISO 105-E04			CHLORINATED WATER ISO 105-E03	
			Dry	Wet																50mg/l	100mg/l
		C.C	C.C	C.C	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	C.C	C.C
0028 BIANCO	class 1	3-4	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	3	2-3
0250 BODY	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	1
0254 SABLE	class 1	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3	1
● 30005 CHIRINGUITO	class 2	1-2	4-5	4-5	4-5	4-5	4-5	4	4	4	4	4	4	4	4	4	4	4	4	1-2	1
30035 ADDICT	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	1-2	1
30038 DREAMLAND	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	1-2	1
4073 VENERE	class 2	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4	4	4-5	4-5	4	4-5	4	4	4-5	4	3-4
50059 VIOLINO	class 2	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	1-2	1
6007 BLU SCURO	class 1	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	2
60271 RACING	class 2	4-5	4	4	4-5	4-5	4-5	4	4	4-5	3-4	4	4-5	4	4	4-5	3-4	4	4-5	2-3	2
60315 FISH	class 1	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	1-2	1
60316 SNAP	class 2	3	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	1
60376 POSTCARD	class 2	2	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	1-2	1
70247 DINOSAURO	class 2	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	2-3
8225 SEGUGIO	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	1
9240 NERO	class 2	>5	4-5	4-5	4-5	3-4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4	4-5	3-4	3

C.C: Colour Change.
S.Co: Staining on Cotton.
S.Pa: Staining on Nylon.
S.Pl: Staining on Polyester.

Testing procedure OEKO-TEX® STANDARD 100 Class 1 and Class 2, please refer to www.oeko-tex.com for more information.

● Colour dyed with a particular fluoro dyestuff that might create a 'blue stains' effect in conditions of high humidity and temperature. This effect can be eliminated: machine wash the garment with soap at 30°C, delicate tumble dry or hang dry.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		