

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT ISO 105-B02	CROCKING ISO 105-X12	WASHING AATC 61/1A	WATER ISO 105-E01	SEA WATER ISO 105-E02	ACID PERSPIRATION PH 5.5 ISO 105-E04	ALKALINE PERSPIRATION PH 8 ISO 105-E04	CHLORINE SENSITIVITY ISO 105-E03
BLACK	6-7	4	4	4	4	4	4	4-5

- C.C: Colour Change.
 S.Co: Staining on Cotton.
 S.Pa: Staining on Nylon.
 S.Pl: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		